

<b>AWI Quick Comparison Guide to Sprayable Finish Systems</b>									
Transparent System Code	TR-0	TR-1	TR-2	TR-3	TR-4	TR-5	TR-6	TR-7	N/A
Opaque System Code	N/A	OP-1	OP-2	OP-3	OP-4	OP-5	OP-6	OP-7	OP-8
Finish System	Synthetic Penet-rating & Simulated Oil	Standard Laquer	Catalyzed Laquer	CAB & Water Acrylic Lacquer	Conversion Varnish	Catalyzed Vinyl	Catalyzed-Polyurethane	Polyester	Polyester / Polyurethane
General durability	5	4	3	4	2	2	1	1	1
Finish clarity	1	1	1	2	3	3	4	2	2
Finished surface flexibility	1	5	3	3	2	2	2	5	4
Stain resistance	5	2	1	2	1	1	1	1	1
Heat resistance	5	5	1	5	1	1	1	1	1
Moisture resistance	5	3	2	3	2	1	1	1	1
Solvent resistance	5	5	2	5	1	1	1	1	1
Toxicity / Risk*	NH	H	H	H	H	H	VH	VH	VH

The numerical ratings are subjective judgements based on the general performance of generic products

\* Toxicity / Risk factor is to the applicator, not the end user

Rating:

1 = Excellent through 5 = Poor

NH = Not Hazardous, H = Hazardous, VH = Very Hazardous